HJS Sintered Metal Filter (SMF®)

Tube Element Catalogue



Innovation through Experience



HJS Emission Technology

HJS Emission Technology stands for nearly 50 years' experience in environmental technologies and is making a significant contribution to meeting newest emission standards and climate targets worldwide.

Our mission is clean air. Integrity and sustainability are the main supports of our commercial action.

With decades of experience in exhaust gas aftertreatment and a comprehensive portfolio of sintered metal filters (SMF®), HJS offers robust and reliable systems for hot gas and liquid filtration.

Whether in energy, chemical, cement and lime or in metal processing industries, HJS provides tailor made filtration solutions for the most demanding industrial applications, setting benchmarks in efficiency, durability, and sustainability.




Sintered Metal Filter Media - SMF®

SMF® material is a high porous, thin sintered metal in which a precisely defined stainless steel powder forms the pore structure, is sintered and supported by an expanded metal

carrier responsible for the required strength. This results in a mechanically and thermally highly stable filter medium with the properties of the three available porosities.




Table of standard Filter-Tubes SMF®-10 and SMF®-20



Diameter (D)	mm	55	77	97	116	116	155	155	194
Length* (L) up to	mm	1,000	1,500	1,500	1,500	5,000	2,500	3,000	3,000
Diameter flange (D1)	mm	75	100	125	150	150	200	200	250
Material thickness flange	mm	3	3	4	4	4	5	5	6
Filtration surface	m²	0.17	0.36	0.45	0.55	0.55	1.46	1.46	1.83
Weight	kg	0.29	0.60	0.75	0.90	0.90	2.41	2.41	3.02
HJS-Article No. SMF®-10		93 80 5510	93 80 7715	93 80 9715	93 80 1115	93 80 1117	93 80 000	93 80 1530	93 80 1930
HJS-Article No. SMF®-20		93 80 5511	93 80 7716	93 80 9716	93 80 1116	93 80 1118	93 80 001	93 80 1531	93 80 1931

^{*} For longer Filter-Tubes, elements can be coupled



Technical Specification

Physical Parameters

Parameter	Unit	Values SMF-10	Values SMF-20	Values SMF-30	
Weight	g/m²	1,650	1,725	1,825	
Thickness	mm	0.38	0.41	0.44	
Porosity	%	45	48	51	
Air permeability @ 1200 Pa	l/dm² min	20	82	137	
Max. Pore size *2	μm	16	38	50	
Mean Flow Pore Size *2	μm	13	27	33	
Min. Pore size *2	μm	12	22	26	
Conductivity @ 20 °C	S/m	0.5 x 10 ⁶	0.5 x 10 ⁶	0.5 x 10 ⁶	
Tensile strength (R _{p0.2})	MPa (x/y)	25 / 36	15 / 35	14 / 33	

 $^{^{*1}}$ ISO 4022 *2 ASTM D6767 (Capillary Flow Test w. IPA)

Filtration Efficiency

Tests according to VDI 3926 and ISO 16890 standards, using 125 mm diameter flat sheet probes, show a F9 filtration efficiency. (according to old EN 779)

Parameter	Unit	Values SMF-10	Values SMF-20	Values SMF-30	Test Method
Efficiency Ulmer Weiß XMF	%	99.999	99.998	99.994	VDI 3926
∆p @ 3.3 cm/s, clean ³³	Pa	236	64	40	VDI 3926
Δp @ 3.3 cm/s, after 30 cycles *3	%	+25	+40	+45	VDI 3926
Efficiency ISO ePM1 fresh anal, F9 *4	80 % - 95 %	85 % @ 4.0 cm/s			ISO 16890


 $^{^{*3}}$ VDI 3926 Dust Ulmer Weis XMF ($x_{50.3}$ =3.3 μ m) \cdot *4 ISO 16890 (sheet test up to Δ p 450 Pa), conditioning in 2/20 cyles acc. VD 3926

In order to demonstrate the general suitability of the SMF® material for applications in the field of gas filtration, basic measurements of the filtration efficiency were carried out

with the material in accordance with the usual standard norms ISO 5011, VDI 3926 and ISO 16890. The results are shown in the table above.


Technical Specification

Pore size distribution




ASTM D6767 (Capillary Flow Test w. IPA)

Differential pressure values SMF®-10, SMF®-20 and SMF®-30



Technical Specification

Physical properties



Alloy	Wet corrosion resistance	Max temperature		
3105	Average	700 °C		
316L	Strong	500 °C		
904L	Very Strong	450 °C		

HJS Sintered Metal Filter, SEM Image

Alloys offer numerous advantages, particularly in enhancing the properties of metals for various applications. One of the key benefits of alloys is their improved chemical resistance compared to pure metals. By combining different elements, alloys can be engineered to resist corrosion, oxidation, and chemical reactions, making them ideal for use in harsh environments. This enhanced chemical stability is crucial in

industries such as aerospace, marine, and chemical processing, where materials are constantly exposed to corrosive substances. Additionally, alloys can be tailored to possess specific properties like increased strength, ductility, and heat resistance, further expanding their versatility and usefulness in various technological applications.

SMF® advantages

- Sintered metal band material for flexible mass production
- Flexible in metal forming and design via pleating, cutting, folding and gluing
- Highest filtration efficiency
- Reduced thickness
- Back flushable in air and liquids
- Catalytic properties through coating (functional surface)
- High temperature durability
- Depending on the application and corrosion perforations other alloys can be used

SMF® exhibit particularly good filtration properties especially for Hot-Gases. The filter material is very well suited for the

dedusting of highly charged gas flows, due to its excellent regeneration behaviour.

The combination of these properties offers the possibility to support the decarbonization of industries, where ${\rm CO_2}$ emissions are difficult to avoid due to the process, namely through

energy recovery or the provision of hot clean filtered process gases for further use. Cooling hot dust-laden process gases can now be eliminated in most cases.

Application areas
































Put your trust in **HJS** and benefit from our extensive experience

- > Products for liquid and hot gas filtration
- > Certified reduction of emissions
- > Products for OEM and retrofit
- > Protection of human health and the environment







Contact Sales: Contact Technology:

Subject to change without notice.

HJS Emission Technology
GmbH & Co. KG

Hubertus Borgmeier Klaus Schrewe

Dieselweg 12 D-58706 Menden/Germany hubertus.borgmeier@hjs.com klaus.schrewe@hjs.com

Phone +49 2373 987-0 Fax +49 2373 987-199 +49 2373 987-282 +49 2373 987-368

E-Mail hjs@hjs.com Internet www.hjs.com

