

PANCAKE COPPER TUBE



UCI manufactures pancake coils with diameters ranging from 4.76 to 22.22 mm and thicknesses between 0.30 to 1.20 mm.

Outside diameter : 4,76 mm - 22,22 mm
Wall Thickness : 0,30 mm - 1,20 mm
Condition : R220

CHEMICAL COMPOSITION

Definition	EN No.	ASTM No
Cu-DHP	CW024A	C12200



MECHANICAL PROPERTIES

Temper	Tensile Strength (Mpa)	Elongation (%)
Annealed	min. 220	min. 40

PANCAKE COIL COPPER TUBE PACKAGING:

Both ends of coils, produced in lengths ranging from 15 to 100 meters depending on the order, are sealed with plastic caps. Each coil is shrink-wrapped and placed in cardboard boxes that fit its size. The boxes are placed on pallets, secured with straps, and stretch-wrapped with PE nylon.

Outside Diameter		Wall Thickness		Lenght
mm	inç	Min (mm)	Max (mm)	m
4,76	3/16	0,30	1,00	15-100
5,00	-	0,30	1,00	15-100
6,00	-	0,30	1,00	15-100
6,35	1/4	0,30	1,00	15-100
7,00	-	0,30	1,00	15-100
7,93	5/16	0,30	1,00	15-100
8,00	-	0,30	1,00	15-100
9,52	3/8	0,30	1,00	15-100
10,00	-	0,30	1,00	15-100
11,00	-	0,30	1,00	15-100
12,00	-	0,30	1,00	15-50
12,70	1/2	0,30	1,00	15-50
13,00	-	0,40	1,00	15-50
13,50	-	0,40	1,00	15-50
14,00	-	0,40	1,00	15-50
15,00	-	0,40	1,00	15-50
15,87	5/8	0,40	1,00	15-50
16,00	-	0,50	1,00	15-50
17,00	-	0,50	1,00	15-50
18,00	-	0,50	1,00	15-50
19,00	-	0,50	1,20	15-25
19,05	3/4	0,50	1,20	15-25
20,00	-	1,00	1,20	15-25
22,00	-	1,00	1,20	15-25
22,22	7/8	1,00	1,20	15-25



• Please contact our Sales Department for dimensions not available in the table.